

Thick-film material combination	Firing	Seebeck coefficient in $\mu\text{V K}^{-1}$	Coefficient of determination R^2
Ag-Ni	sequential fired	23.9	0.9956
Ag-Pt	sequential fired	8.0	0.9799
Au-Pt	sequential fired	10.7	0.9912
Pd-Ag	sequential fired	6.6	0.9982
Cu-Ni	sequential fired	15.9	0.9959
Pd-Pt	co-fired	2.5	0.9976
Pd-Pt	sequential fired	1.06	0.9687
Pt-PtRh ₁₀	co-fired	4.79	0.9860
Pt-PtRh ₁₀	sequential fired	4.82	0.9870